



70411

Description

A 40 durometer, white, addition cured silicone rubber compound that meets ASTM D2000M3FE408 (Z1 - tensile strength = 1013 psi; Z2 - heat age tensile strength = -45%).

70411 is designed for optimal re-sealability, low bleed, and ease of puncture.

Physical Properties	Actual Value	Spec. Value
Original Properties - cured 20 mins @ 320F ; postcured 4 hrs @ 200C		
Specific Gravity	1.10	1.10 +/- .03
Hardness (Shore A)	41.0	40 +/- 5
Tensile Strength	1013 psi (6.98 Mpa)	900 psi min.
Elongation	610%	500% min.
100% Modulus	155 psi (1.07 Mpa)	
Tear Strength, Die C	94.2 ppi (16.48 kN/m)	80 ppi min.
Compression Set (22 hrs @ 175 C)	10.12%	
Heat Aging (70 hrs @ 200C)		
Hardness (Shore A)	42.5	
Change	+1.5 pts	
Tensile Strength	555 psi (3.83 Mpa)	
Tensile Strength change	- 45.21%	
Elongation	377%	
Elongation Change	-38.20%	



All information supplied by or on behalf of Pawling Corporation in relation to its products, whether in the nature of data, recommendations or otherwise, is believed reliable, but Pawling Corporation assumes no liability whatsoever in respect of application, processing or use made of the information, or any consequences thereof.