



FEP

Description

FEP is a transparent, fluorocarbon film that has excellent chemical and temperature resistance. It is resistant to practically all chemicals other than molten alkali metals, gaseous fluorine, and certain complex halogenated compounds such as chlorine trifluoride at elevated temperatures and pressures.

FEP exhibits very low permeability to liquids, gases, moisture, and organic vapors. For septa, it is predominantly used in conjunction with Butyl and Natural Rubber polymers.

Color: Clear
Thickness: .002 (2 mil)

Mechanical Properties

Actual Value

Sample Thickness	.001 (1 mil)
Tensile Strength at Break	3000 psi
Elongation	300%
Tear Strength - Initial (Graves)	270g force

Thermal

Melt Point 500-536°F (260-280°C)

Information Supplied Courtesy of Dupont.



All information supplied by or on behalf of Pawling Corporation in relation to its products, whether in the nature of data, recommendations or otherwise, is believed reliable, but Pawling Corporation assumes no liability whatsoever in respect of application, processing or use made of the information, or any consequences thereof.